



Chemical Compatibility for CPVC Corzan Pipe and fittings

Note that the effect of any chemical on CPVC Corzan pipe systems may be dependent on factors such as temperature, pressure, concentrations, abrasiveness etc.

Acetaldehyde	Not Recommended
Acetamide	No Data
Acetate Solvent	Poor
Acetic Acid	Poor
Acetic Acid 20%	Excellent
Acetic Acid 80%	Poor
Acetic Acid, Glacial	Good up to 22oC
Acetic Anhydride	Not Recommended
Acetone	Not Recommended
Acetyl Bromide	No Data
Acetyl Chloride (dry)	Poor
Acetylene	Poor
Acrylonitrile	Excellent
Adipic Acid	Excellent up to 48oC
Alcohols: Amyl	Excellent up to 48oC
Alcohols: Benzyl	Excellent
Alcohols: Butyl	Excellent up to 48oC
Alcohols: Diacetone	No Data
Alcohols: Ethyl	Good
Alcohols: Hexyl	No Data
Alcohols: Isobutyl	No Data
Alcohols: Isopropyl	Poor
Alcohols: Methyl	Excellent
Alcohols: Octyl	Good up to 22oC
Alcohols: Propyl	Excellent up to 48oC
Aluminum Chloride	Excellent
Aluminum Chloride 20%	Excellent
Aluminum Fluoride	Excellent
Aluminum Hydroxide	Excellent
Aluminum Nitrate	Excellent
Aluminum Potassium Sulfate 10%	Good
Aluminum Potassium Sulfate 100%	Good
Aluminum Sulfate	Excellent up to 48oC
Alums	Excellent



Plastic Pipe Shop Ltd.

Tel: 01786 472850 sales@plasticpipeshop.co.uk www.plasticpipeshop.co.uk

Amines	Not Recommended
Ammonia 10%	Excellent
Ammonia Nitrate	Good
Ammonia, anhydrous	Excellent up to 22oC
Ammonia, liquid	Excellent
Ammonium Acetate	Excellent
Ammonium Bifluoride	Excellent
Ammonium Carbonate	Excellent
Ammonium Caseinate	No Data
Ammonium Chloride	Excellent up to 48oC
Ammonium Hydroxide	Excellent
Ammonium Nitrate	Excellent up to 48oC
Ammonium Oxalate	No Data
Ammonium Persulfate	Excellent
Ammonium Phosphate, Dibasic	Excellent
Ammonium Phosphate, Monobasic	Excellent
Ammonium Phosphate, Tribasic	Excellent
Ammonium Sulfate	Excellent
Ammonium Sulfite	Excellent
Ammonium Thiosulfate	No Data
Amyl Acetate	Not Recommended
Amyl Alcohol	Excellent up to 48oC
Amyl Chloride	Poor
Aniline	Good up to 48oC
Aniline Hydrochloride	Not Recommended
Antifreeze	Excellent
Antimony Trichloride	Excellent up to 48oC
Aqua Regia (80% HCl, 20% HNO ₃)	Poor to 22oC (not recommended higher)
Arochlor 1248	No Data
Aromatic Hydrocarbons	Not Recommended
Arsenic Acid	Excellent up to 22oC
Arsenic Salts	No Data
Asphalt	Excellent up to 48oC
Barium Carbonate	Excellent up to 48oC
Barium Chloride	Excellent up to 22oC
Barium Cyanide	Not Recommended
Barium Hydroxide	Excellent up to 48oC
Barium Nitrate	Excellent
Barium Sulfate	Good up to 22oC
Barium Sulfide	Excellent up to 48oC



Plastic Pipe Shop Ltd.

Tel: 01786 472850 sales@plasticpipeshop.co.uk www.plasticpipeshop.co.uk

Beer	Excellent up to 48oC
Beet Sugar Liquids	Excellent up to 48oC
Benzaldehyde	Not Recommended
Benzene	Not Recommended
Benzene Sulfonic Acid	Not Recommended
Benzoic Acid	Excellent up to 22oC
Benzol	No Data
Benzonitrile	No Data
Benzyl Chloride	No Data
Bleaching Liquors	No Data
Borax (Sodium Borate)	Excellent
Boric Acid	Excellent
Brewery Slop	No Data
Bromine	Not Recommended
Butadiene	Excellent up to 22oC
Butane	Poor to 22oC (not recommended higher)
Butanol (Butyl Alcohol)	Excellent
Butter	No Data
Buttermilk	Excellent up to 22oC
Butyl Amine	No Data
Butyl Ether	Not Recommended
Butyl Phthalate	Not Recommended
Butylacetate	Poor to 22oC (not recommended higher)
Butylene	Excellent
Butyric Acid	Not Recommended
Calcium Bisulfate	No Data
Calcium Bisulfide	Excellent up to 22oC
Calcium Bisulfite	Excellent up to 22oC
Calcium Carbonate	Excellent
Calcium Chlorate	Excellent up to 22oC
Calcium Chloride	Excellent up to 48oC
Calcium Hydroxide	Excellent up to 48oC
Calcium Hypochlorite	Good up to 22oC
Calcium Nitrate	Excellent up to 48oC
Calcium Oxide	Excellent
Calcium Sulfate	Excellent up to 48oC
Calgon	No Data
Cane Juice	Excellent up to 48oC
Carbolic Acid (Phenol)	Good up to 22oC
Carbon Bisulfide	Not Recommended



Plastic Pipe Shop Ltd.

Tel: 01786 472850 sales@plasticpipeshop.co.uk www.plasticpipeshop.co.uk

Carbon Dioxide (dry)	Excellent
Carbon Dioxide (wet)	Excellent
Carbon Disulfide	Not Recommended
Carbon Monoxide	Excellent up to 48oC
Carbon Tetrachloride	Not Recommended
Carbon Tetrachloride (dry)	No Data
Carbon Tetrachloride (wet)	Not Recommended
Carbonated Water	Excellent
Carbonic Acid	Excellent
Catsup	Excellent
Chloric Acid	Excellent
Chlorinated Glue	No Data
Chlorine (dry)	Not Recommended
Chlorine Water	Excellent up to 48oC
Chlorine, Anhydrous Liquid	Not Recommended
Chloroacetic Acid	Not Recommended
Chlorobenzene (Mono)	Not Recommended
Chlorobromomethane	No Data
Chloroform	Not Recommended
Chlorosulfonic Acid	Not Recommended
Chocolate Syrup	No Data
Chromic Acid 10%	Excellent up to 48oC
Chromic Acid 30%	Excellent up to 22oC
Chromic Acid 5%	Excellent
Chromic Acid 50%	Not Recommended
Chromium Salts	No Data
Cider	No Data
Citric Acid	Good up to 48oC
Citric Oils	No Data
Cloroxr (Bleach)	Excellent
Coffee	Excellent
Copper Chloride	Excellent
Copper Cyanide	Excellent
Copper Fluoborate	Excellent up to 22oC
Copper Nitrate	Excellent
Copper Sulfate >5%	Excellent
Copper Sulfate 5%	Excellent
Cream	Excellent
Cresols	Not Recommended
Cresylic Acid	Not Recommended



Plastic Pipe Shop Ltd.

Tel: 01786 472850 sales@plasticpipeshop.co.uk www.plasticpipeshop.co.uk

Cupric Acid	No Data
Cyanic Acid	No Data
Cyclohexane	Not Recommended
Cyclohexanone	Not Recommended
Detergents	Excellent
Diacetone Alcohol	Not Recommended
Dichlorobenzene	Not Recommended
Dichloroethane	Not Recommended
Diesel Fuel	Excellent up to 22oC
Diethyl Ether	Not Recommended
Diethylamine	Not Recommended
Diethylene Glycol	Excellent up to 22oC
Dimethyl Aniline	Not Recommended
Dimethyl Formamide	Not Recommended
Diphenyl	No Data
Diphenyl Oxide	No Data
Dyes	No Data
Epsom Salts (Magnesium Sulfate)	Excellent up to 22oC
Ethane	Excellent up to 22oC
Ethanol	Good
Ethanolamine	No Data
Ether	Not Recommended
Ethyl Acetate	Not Recommended
Ethyl Benzoate	Not Recommended
Ethyl Chloride	Not Recommended
Ethyl Ether	Not Recommended
Ethyl Sulfate	No Data
Ethylene Bromide	Not Recommended
Ethylene Chloride	Not Recommended
Ethylene Chlorohydrin	Not Recommended
Ethylene Diamine	Not Recommended
Ethylene Dichloride	Not Recommended
Ethylene Glycol	Excellent
Ethylene Oxide	Poor to 22oC (not recommended higher)
Fatty Acids	Excellent
Ferric Chloride	Excellent
Ferric Nitrate	Excellent
Ferric Sulfate	Excellent
Ferrous Chloride	Excellent
Ferrous Sulfate	Excellent



Plastic Pipe Shop Ltd.

Tel: 01786 472850 sales@plasticpipeshop.co.uk www.plasticpipeshop.co.uk

Fluoboric Acid	Excellent up to 48oC
Fluorine	Not Recommended
Fluosilicic Acid	Excellent
Formaldehyde 100%	Excellent
Formaldehyde 40%	Excellent up to 48oC
Formic Acid	Excellent up to 48oC
Freon 113	Good
Freon 12	Excellent up to 48oC
Freon 22	Good
Freon TF	Good
Freonr 11	Excellent up to 48oC
Fruit Juice	Excellent
Fuel Oils	No Data
Furan Resin	No Data
Furfural	Not Recommended
Gallic Acid	Poor
Gasoline (high-aromatic)	Poor to 22oC (not recommended higher)
Gasoline, leaded, ref.	No Data
Gasoline, unleaded	Poor
Gelatin	Excellent up to 48oC
Glucose	Excellent up to 48oC
Glue, P.V.A.	Excellent
Glycerin	Excellent
Glycolic Acid	Excellent
Gold Monocyanide	No Data
Grape Juice	Excellent
Grease	No Data
Heptane	Excellent
Hexane	Good up to 22oC
Honey	No Data
Hydraulic Oil (Petro)	No Data
Hydraulic Oil (Synthetic)	No Data
Hydrazine	Not Recommended
Hydrobromic Acid 100%	Excellent up to 48oC
Hydrobromic Acid 20%	Excellent
Hydrochloric Acid 100%	Excellent
Hydrochloric Acid 20%	Excellent up to 48oC
Hydrochloric Acid 37%	Excellent up to 48oC
Hydrochloric Acid, Dry Gas	Excellent
Hydrocyanic Acid	Excellent



Plastic Pipe Shop Ltd.

Tel: 01786 472850 sales@plasticpipeshop.co.uk www.plasticpipeshop.co.uk

Hydrocyanic Acid (Gas 10%)	Excellent
Hydrofluoric Acid 100%	Poor to 22oC (not recommended higher)
Hydrofluoric Acid 20%	Poor to 22oC (not recommended higher)
Hydrofluoric Acid 50%	Poor to 22oC (not recommended higher)
Hydrofluoric Acid 75%	Poor to 22oC (not recommended higher)
Hydrofluosilicic Acid 100%	No Data
Hydrofluosilicic Acid 20%	Excellent
Hydrogen Gas	Excellent up to 48oC
Hydrogen Peroxide 10%	Excellent
Hydrogen Peroxide 100%	Excellent
Hydrogen Peroxide 30%	Excellent
Hydrogen Peroxide 50%	Excellent
Hydrogen Sulfide (aqua)	Excellent
Hydrogen Sulfide (dry)	Excellent
Hydroquinone	Excellent
Hydroxyacetic Acid 70%	Excellent
Ink	No Data
Iodine	Not Recommended
Iodine (in alcohol)	No Data
Iodoform	No Data
Isooctane	No Data
Isopropyl Acetate	No Data
Isopropyl Ether	No Data
Isotane	No Data
Jet Fuel (JP3, JP4, JP5)	No Data
Kerosene	No Data
Ketones	No Data
Lacquer Thinners	No Data
Lacquers	No Data
Lactic Acid	Excellent up to 22oC
Lard	No Data
Latex	No Data
Lead Acetate	Excellent up to 48oC
Lead Nitrate	Excellent up to 48oC
Lead Sulfamate	No Data
Ligroin	No Data
Lime	No Data
Linoleic Acid	Excellent up to 48oC
Lithium Chloride	Excellent up to 48oC
Lithium Hydroxide	No Data



Plastic Pipe Shop Ltd.

Tel: 01786 472850 sales@plasticpipeshop.co.uk www.plasticpipeshop.co.uk

Lubricants	No Data
Lye: Ca(OH) ₂ Calcium Hydroxide	Excellent up to 48oC
Lye: KOH Potassium Hydroxide	Excellent
Lye: NaOH Sodium Hydroxide	Excellent
Magnesium Bisulfate	No Data
Magnesium Carbonate	Excellent up to 48oC
Magnesium Chloride	Excellent
Magnesium Hydroxide	Excellent
Magnesium Nitrate	Excellent
Magnesium Oxide	No Data
Magnesium Sulfate (Epsom Salts)	Excellent up to 22oC
Maleic Acid	Excellent
Maleic Anhydride	No Data
Malic Acid	No Data
Manganese Sulfate	Excellent
Mash	No Data
Mayonnaise	No Data
Melamine	Excellent up to 48oC
Mercuric Chloride (dilute)	Excellent
Mercuric Cyanide	Excellent
Mercurous Nitrate	Excellent up to 48oC
Mercury	Excellent
Methane	No Data
Methanol (Methyl Alcohol)	Excellent
Methyl Acetate	No Data
Methyl Acetone	No Data
Methyl Acrylate	No Data
Methyl Alcohol 10%	Excellent
Methyl Bromide	Not Recommended
Methyl Butyl Ketone	No Data
Methyl Cellosolve	Not Recommended
Methyl Chloride	Not Recommended
Methyl Dichloride	No Data
Methyl Ethyl Ketone	Not Recommended
Methyl Ethyl Ketone Peroxide	No Data
Methyl Isobutyl Ketone	Not Recommended
Methyl Isopropyl Ketone	No Data
Methyl Methacrylate	No Data
Methylamine	No Data
Methylene Chloride	Not Recommended



Plastic Pipe Shop Ltd.

Tel: 01786 472850 sales@plasticpipeshop.co.uk www.plasticpipeshop.co.uk

Milk	Excellent
Mineral Spirits	Excellent
Molasses	Excellent
Monochloroacetic acid	No Data
Monoethanolamine	No Data
Morpholine	No Data
Motor oil	Excellent
Mustard	Excellent
Naphtha	Excellent
Naphthalene	Not Recommended
Natural Gas	No Data
Nickel Chloride	Excellent
Nickel Nitrate	Excellent up to 48oC
Nickel Sulfate	Excellent
Nitrating Acid (< 15% HNO3)	No Data
Nitrating Acid (> 15% H2SO4)	No Data
Nitrating Acid (S1% Acid)	No Data
Nitrating Acid (S15% H2SO4)	No Data
Nitric Acid (20%)	Excellent up to 48oC
Nitric Acid (50%)	Good up to 22oC
Nitric Acid (5-10%)	Excellent
Nitric Acid (Concentrated)	Not Recommended
Nitrobenzene	Not Recommended
Nitrogen Fertilizer	No Data
Nitromethane	No Data
Nitrous Acid	Excellent
Nitrous Oxide	No Data
Oils: Aniline	No Data
Oils: Anise	No Data
Oils: Bay	No Data
Oils: Bone	No Data
Oils: Castor	Poor
Oils: Cinnamon	No Data
Oils: Citric	No Data
Oils: Clove	No Data
Oils: Coconut	Excellent up to 22oC
Oils: Cod Liver	Excellent up to 22oC
Oils: Corn	No Data
Oils: Cottonseed	Excellent
Oils: Creosote	No Data



Plastic Pipe Shop Ltd.

Tel: 01786 472850 sales@plasticpipeshop.co.uk www.plasticpipeshop.co.uk

Oils: Diesel Fuel (20, 30, 40, 50)	No Data
Oils: Fuel (1, 2, 3, 5A, 5B, 6)	No Data
Oils: Ginger	No Data
Oils: Hydraulic Oil (Petro)	No Data
Oils: Hydraulic Oil (Synthetic)	No Data
Oils: Lemon	No Data
Oils: Linseed	Poor
Oils: Mineral	Excellent
Oils: Olive	Poor
Oils: Orange	No Data
Oils: Palm	Excellent
Oils: Peanut	Poor
Oils: Peppermint	No Data
Oils: Pine	Excellent
Oils: Rapeseed	Excellent
Oils: Rosin	No Data
Oils: Sesame Seed	Excellent
Oils: Silicone	Excellent
Oils: Soybean	Excellent up to 48oC
Oils: Sperm (whale)	Excellent
Oils: Tanning	No Data
Oils: Transformer	Excellent
Oils: Turbine	Excellent
Oleic Acid	Excellent
Oleum 100%	Not Recommended
Oleum 25%	Not Recommended
Oxalic Acid (cold)	Excellent
Ozone	Excellent
Palmitic Acid	Excellent up to 22oC
Paraffin	Excellent
Pentane	No Data
Perchloric Acid	Excellent up to 22oC
Perchloroethylene	Poor to 22oC (not recommended higher)
Petrolatum	No Data
Petroleum	Excellent up to 48oC
Phenol (10%)	Excellent up to 22oC
Phenol (Carbolic Acid)	Good up to 22oC
Phosphoric Acid (>40%)	Excellent
Phosphoric Acid (crude)	No Data
Phosphoric Acid (molten)	No Data



Plastic Pipe Shop Ltd.

Tel: 01786 472850 sales@plasticpipeshop.co.uk www.plasticpipeshop.co.uk

Phosphoric Acid (S40%)	Excellent
Phosphoric Acid Anhydride	No Data
Phosphorus	Good up to 220C
Phosphorus Trichloride	Not Recommended
Photographic Developer	Excellent
Photographic Solutions	Excellent
Phthalic Acid	Good
Phthalic Anhydride	Not Recommended
Picric Acid	Not Recommended
Antimony Plating 130°F	Excellent
Arsenic Plating 110°F	Excellent
Brass Plating: High-Speed Brass Bath 110°F	Excellent
Brass Plating: Regular Brass Bath 100°F	Excellent
Bronze Plating: Cu-Cd Bronze Bath R.T.	Excellent
Bronze Plating: Cu-Sn Bronze Bath 160°F	Not Recommended
Bronze Plating: Cu-Zn Bronze Bath 100°F	Excellent
Cadmium Plating: Cyanide Bath 90°F	Excellent
Cadmium Plating: Fluoborate Bath 100°F	Excellent
Chromium Plating: Barrel Chrome Bath 95°F	Excellent
Chromium Plating: Black Chrome Bath 115°F	Excellent
Chromium Plating: Chromic-Sulfuric Bath 130°F	Excellent
Chromium Plating: Fluoride Bath 130°F	Excellent
Chromium Plating: Fluosilicate Bath 95°F	Excellent
Copper Plating (Acid): Copper Fluoborate Bath 120°F	Excellent
Copper Plating (Acid): Copper Sulfate Bath R.T.	Excellent
Copper Plating (Cyanide): Copper Strike Bath 120°F	Excellent
Copper Plating (Cyanide): High-Speed Bath 180°F	Not Recommended
Copper Plating (Cyanide): Rochelle Salt Bath 150°F	Not Recommended
Copper Plating (Misc): Copper (Electroless)	Excellent
Copper Plating (Misc): Copper Pyrophosphate	Excellent
Gold Plating: Acid 75°F	Excellent
Gold Plating: Cyanide 150°F	Not Recommended
Gold Plating: Neutral 75°F	Excellent
Indium Sulfamate Plating R.T.	Excellent
Iron Plating: Ferrous Am Sulfate Bath 150°F	Not Recommended
Iron Plating: Ferrous Chloride Bath 190°F	Not Recommended
Iron Plating: Ferrous Sulfate Bath 150°F	Not Recommended
Iron Plating: Fluoborate Bath 145°F	Not Recommended
Iron Plating: Sulfamate 140°F	Excellent
Iron Plating: Sulfate-Chloride Bath 160°F	Not Recommended



Plastic Pipe Shop Ltd.

Tel: 01786 472850 sales@plasticpipeshop.co.uk www.plasticpipeshop.co.uk

Lead Fluoborate Plating	Excellent
Nickel Plating: Electroless 200°F	Not Recommended
Nickel Plating: Fluoborate 100-170°F	Excellent
Nickel Plating: High-Chloride 130-160°F	Not Recommended
Nickel Plating: Sulfamate 100-140°F	Excellent
Nickel Plating: Watts Type 115-160°F	Not Recommended
Rhodium Plating 120°F	Excellent
Silver Plating 80-120°F	Excellent
Tin-Fluoborate Plating 100°F	Excellent
Tin-Lead Plating 100°F	Excellent
Zinc Plating: Acid Chloride 140°F	Excellent
Zinc Plating: Acid Fluoborate Bath R.T.	Excellent
Zinc Plating: Acid Sulfate Bath 150°F	Not Recommended
Zinc Plating: Alkaline Cyanide Bath R.T.	Excellent
Potash (Potassium Carbonate)	Excellent
Potassium Bicarbonate	Excellent
Potassium Bromide	Excellent
Potassium Chlorate	Excellent
Potassium Chloride	Excellent
Potassium Chromate	Excellent
Potassium Cyanide Solutions	Excellent
Potassium Dichromate	Excellent
Potassium Ferricyanide	Excellent
Potassium Ferrocyanide	Good
Potassium Hydroxide (Caustic Potash)	Excellent
Potassium Hypochlorite	No Data
Potassium Iodide	Excellent
Potassium Nitrate	Excellent
Potassium Oxalate	No Data
Potassium Permanganate	Excellent up to 22oC
Potassium Sulfate	Excellent
Potassium Sulfide	Excellent up to 48oC
Propane (liquefied)	Excellent up to 22oC
Propylene	No Data
Propylene Glycol	Poor to 22oC (not recommended higher)
Pyridine	Not Recommended
Pyrogallic Acid	Excellent
Resorcinal	No Data
Rosins	Poor to 22oC (not recommended higher)
Rum	Excellent



Plastic Pipe Shop Ltd.

Tel: 01786 472850 sales@plasticpipeshop.co.uk www.plasticpipeshop.co.uk

Rust Inhibitors	No Data
Salad Dressings	No Data
Salicylic Acid	No Data
Salt Brine (NaCl saturated)	Excellent up to 48oC
Sea Water	Excellent
Shellac (Bleached)	No Data
Shellac (Orange)	No Data
Silicone	Excellent
Silver Bromide	No Data
Silver Nitrate	Excellent up to 22oC
Soap Solutions	Excellent
Soda Ash (see Sodium Carbonate)	Excellent
Sodium Acetate	Excellent
Sodium Aluminate	No Data
Sodium Benzoate	Excellent up to 48oC
Sodium Bicarbonate	Excellent up to 48oC
Sodium Bisulfate	Excellent up to 48oC
Sodium Bisulfite	Excellent up to 48oC
Sodium Borate (Borax)	Excellent up to 48oC
Sodium Bromide	Excellent up to 48oC
Sodium Carbonate	Excellent up to 48oC
Sodium Chlorate	Excellent up to 22oC
Sodium Chloride	Excellent up to 48oC
Sodium Chromate	No Data
Sodium Cyanide	Excellent up to 48oC
Sodium Ferrocyanide	Excellent
Sodium Fluoride	Excellent up to 48oC
Sodium Hydrosulfite	Poor
Sodium Hydroxide (20%)	Excellent
Sodium Hydroxide (50%)	Excellent
Sodium Hydroxide (80%)	Excellent
Sodium Hypochlorite (<20%)	Excellent
Sodium Hypochlorite (100%)	Poor to 48oC (not recommended higher)
Sodium Hyposulfate	No Data
Sodium Metaphosphate	Excellent up to 22oC
Sodium Metasilicate	Excellent
Sodium Nitrate	Excellent
Sodium Perborate	Excellent up to 22oC
Sodium Peroxide	Excellent up to 48oC
Sodium Polyphosphate	Excellent up to 22oC



Plastic Pipe Shop Ltd.

Tel: 01786 472850 sales@plasticpipeshop.co.uk www.plasticpipeshop.co.uk

Sodium Silicate	Excellent up to 48oC
Sodium Sulfate	Excellent up to 48oC
Sodium Sulfide	Excellent up to 48oC
Sodium Sulfite	Excellent up to 48oC
Sodium Tetraborate	Excellent
Sodium Thiosulfate (hypo)	Excellent up to 48oC
Sorghum	No Data
Soy Sauce	No Data
Stannic Chloride	Excellent up to 48oC
Stannic Fluoborate	No Data
Stannous Chloride	Excellent up to 48oC
Starch	Excellent
Stearic Acid	Good up to 48oC
Stoddard Solvent	Poor to 22oC (not recommended higher)
Styrene	Not Recommended
Sugar (Liquids)	No Data
Sulfate (Liquors)	Good
Sulfur Chloride	Poor to 22oC (not recommended higher)
Sulfur Dioxide	Excellent up to 48oC
Sulfur Dioxide (dry)	Excellent up to 48oC
Sulfur Hexafluoride	No Data
Sulfur Trioxide	Excellent
Sulfur Trioxide (dry)	Excellent
Sulfuric Acid (<10%)	Excellent
Sulfuric Acid (10-75%)	Excellent
Sulfuric Acid (75-100%)	Poor
Sulfuric Acid (cold concentrated)	Not Recommended
Sulfuric Acid (hot concentrated)	Not Recommended
Sulfurous Acid	Excellent up to 48oC
Sulfuryl Chloride	No Data
Tallow	No Data
Tannic Acid	Excellent up to 22oC
Tanning Liquors	Excellent up to 22oC
Tartaric Acid	Excellent up to 22oC
Tetrachloroethane	Poor
Tetrachloroethylene	Not Recommended
Tetrahydrofuran	Not Recommended
Tin Salts	No Data
Toluene (Toluol)	Not Recommended
Tomato Juice	No Data



Plastic Pipe Shop Ltd.

Tel: 01786 472850 sales@plasticpipeshop.co.uk www.plasticpipeshop.co.uk

Trichloroacetic Acid	No Data
Trichloroethane	No Data
Trichloroethylene	Not Recommended
Trichloropropane	No Data
Tricresylphosphate	Not Recommended
Triethylamine	Excellent
Trisodium Phosphate	Excellent
Turpentine	Excellent
Urea	Excellent
Uric Acid	No Data
Urine	Excellent
Varnish	No Data
Vegetable Juice	No Data
Vinegar	Excellent
Vinyl Acetate	Not Recommended
Vinyl Chloride	Not Recommended
Water, Acid, Mine	Excellent
Water, Deionized	Excellent
Water, Distilled	Excellent
Water, Fresh	Excellent
Water, Salt	Excellent
Weed Killers	No Data
Whey	No Data
Whiskey & Wines	Excellent up to 48oC
White Liquor (Pulp Mill)	Excellent
White Water (Paper Mill)	No Data
Xylene	Not Recommended
Zinc Chloride	Excellent
Zinc Hydrosulfite	No Data
Zinc Sulfate	Excellent

IMPORTANT NOTES

This information has been supplied to Plastic Pipe Shop Ltd by its suppliers and other reputable sources. The information should only be used as a guide to choosing the correct material for your application. The ratings for each chemical are generally based on a 48 hour exposure period. There is no data for effects beyond this timescale. It is recommended that before any ordering and installations are carried out, that the materials are tested in the specific conditions of the application in which they are to be used.



Plastic Pipe Shop Ltd.

Tel: 01786 472850 sales@plasticpipeshop.co.uk www.plasticpipeshop.co.uk

Plastic Pipe Shop Ltd does not guarantee (neither express nor implied) that this information is accurate or complete. Further, Plastic Pipe Shop Ltd does not, by way of this information make any recommendation that any material is suitable for any purpose.